


Multi-Color Fluorescent / Phosphorescent Polyimides Exhibiting Very Large Stokes Shifts and Their Application for Solar Spectral Conversion (*invited*)

Shinji ANDO

Department of Chemical Science & Engineering, Tokyo Institute of Technology (Tokyo Tech)

E-mail : sando@polymer.titech.ac.jp

Polymeric materials exhibiting fluorescent and phosphorescent emission are expected to be applied for wavelength down-converters in a wide range of applications such as flat panel displays, flexible displays, photovoltaic devices, and crop cultivators. However, conventional fluorescent polymers consisting of π -conjugated sequences do not have sufficient mechanical properties and thermal, environmental, and radiation stabilities. In 2009, we have reported that a series of semi-aromatic polyimide (PI) films exhibit strong blue to green fluorescent emission. The high quantum efficiency ($\Phi > 0.11$) of the PIs was attributable not only to the suppression of charge-transfer (CT) interactions, but also to the enhancement of the locally excited π - π^* transition and effective suppression of concentration quenching by steric effects. We have recently reported a series of imides and PIs containing one or two -OH groups which form ideal intramolecular hydrogen bonds between the -OH and C=O groups exhibit strong and tunable multi-color (blue, green, yellow, to deep red) fluorescence with very large Stokes shifts ($7,655\sim 11,394\text{ cm}^{-1}$) via excited-state intramolecular proton transfer (ESIPT). Moreover, the corresponding deprotonated mono- and di-anion species are formed in basic conditions, which are characterized by visible halochromism in their absorption and emission spectra. Copolymer films derived from the blue- and red-fluorescent PIs exhibit strong absorption in the UV region, and the transmission intensities in the visible blue and orange regions are obviously enhanced by $\sim 16\%$ due to the fluorescent emission. Very recently, we have developed highly phosphorescent PIs by introducing heavy halogens (Br, I) in the skeletal structures of dianhydrides. Judicious design of highly fluorescent / phosphorescent PIs provides promising materials for fabricating tough and flexible wavelength converters which efficiently absorb UV light from the sun or LEDs and emit tunable visible to near-infrared radiation without consuming any external energy.



Keywords

Polyimide, Fluorescence, Room temperature phosphorescence, Excited state intramolecular proton transfer, Heavy halogen, Stokes shift